



The Chemical Company

PRODUCT DATA

3 03 01 00

Maintenance of Concrete

EMACO® T430

Rapid-strength repair mortar with extended working time

Description

Emaco® T430 repair mortar is a one-component high-performance cementitious product. It produces high early strengths at a wide range of temperatures and can be placed into service for standard rubber-tire traffic in as little as 6 hours. Emaco® T430 is specially suited for hot-weather applications when an extended working time is required.

Yield

One 55 lb (25 kg) bag of Emaco® T430 mixed with the required water will cover approximately 9.6 ft² (0.9 m²) at a 1/2" (13 mm) thickness or approximately 0.40 ft³ (0.011 m³).

With an extension of 55% aggregate, 3/8" in size, the yield is approximately 0.58 ft³ (0.016 m³).

For estimating purposes, 46 bags of Emaco® T430 plus 1,380 lbs of clean, coarse 3/8" SSD aggregate yields approximately 1 yd³ (60 bags of Emaco® T430 repair mortar plus 820 kg of 9.5 mm SSD aggregate yields approximately 1 m³).

Packaging

55 lb (25 kg) multi-wall bags
3,300 lb (1,500 kg) bulk bags available by special order

Shelf Life

6 months when properly stored

Storage

Store in unopened containers in a clean, dry area between 45 and 90° F (7 and 32° C).

Features

- Fast curing
- Wide temperature application range (20 to 100° F [-7 to 38° C])
- One component
- Rapid high early strength (1,000 psi [7 MPa] in 3 hours)
- Excellent bond
- Resistant to damage caused by freeze/thaw cycles
- Ample working time for a rapid repair mortar
- Extendable up to 55% by weight for deep patches

Benefits

- Will accept an epoxy coating within 6 hours
- Reduces dependency on weather
- Just add water and mix
- Rapidly returns repaired areas to service
- No bonding agent required
- Usable in most environments
- Helps ensure proper placement
- Economical repairs

Where to Use

APPLICATION

- Concrete floor repairs
- Full-depth slab repairs
- Concrete pavement-joint repairs
- Heavy industrial repairs
- Horizontal patching
- Formed vertical repairs requiring minimal downtime or quick coating
- Parking structure decks and ramps
- Highway repairs
- Wastewater-treatment facilities
- Truck docks

How to Apply

Surface Preparation

CONCRETE

1. Perform surface preparation in compliance with ICRI Technical Guideline No. 03730 "Guide for Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion."

2. Remove all unsound or delaminated concrete, providing a minimum of 1/4" (6 mm) substrate profile and 3/4" (19 mm) clearance behind corroded reinforcing steel.
3. Sawcut the perimeter of the area being repaired to a minimum depth of 1" (25 mm) to prevent featheredges. Do not cut the reinforcement.
4. After removal of concrete but before placement, mechanically abrade the concrete surface to remove all bond-inhibiting materials and to provide additional mechanical bond. Do not use a method of surface preparation that will fracture the concrete. Verify the absence of microcracking or bruising in accordance with ICRI Guideline No. 03732.
5. Unless a bonding agent will be used, presoak the prepared concrete surface to a saturated surface-dry (SSD) condition.



Technical Data

Composition

Emaco® T430 contains modified cementitious binder, aggregate, and additives.

Typical Properties

PROPERTY	VALUE
Water %, by weight	8.0
Flow at 5 drops	100
Working time, min, at 70° F (21° C)	45

Test Data¹

PROPERTY	RESULTS	TEST METHODS		
Compressive strength , psi (MPa), 70° F (21° C)		ASTM C 109		
3 hrs	1,000 (7)			
24 hrs	4,500 (31)			
7 days	7,800 (54)			
28 days	9,000(62)			
Setting time , min		ASTM C 266 at 72° F (22° C)		
	50° F (10° C)	70° F (21° C)	90° F (32° C)	
Initial set	140	75	65	
Final set	160	90	75	
	1 Day Psi (MPa)	7 Days Psi (MPa)	28 Days Psi (MPa)	
Flexural strength	580 (4.0)	880 (6.1)	1,150 (7.9)	ASTM C 348
Splitting tensile	550 (3.8)	1,100 (7.6)	1,250 (8.6)	ASTM C 496
Slant shear bond	1,800 (12.4)	3,000 (20.7)	3,360 (23.2)	ASTM C 882
Direct shear bond	150 (1.0)	390 (2.7)	450 (3.1)	Michigan DOT
Direct tensile bond	100 (0.7)	170 (1.2)	290 (2.0)	BASF method
Modulus of elasticity , psi (GPa), at 28 Days	5.1 x 10 ⁶ (35)			
Abrasion resistance , in (cm) of wear, 28 day air-cured sample				ASTM C 779 A
30 min	0.0120 (0.0305)			
60 min	0.0240 (0.0610)			
Freeze/thaw resistance , % RDM	98.5			ASTM C 666 A
Rapid chloride permeability² , coulombs	990 (very low)			AASHTO-T277 / ASTM C 1202
Scaling resistance , weight loss, lb/ft ²				ASTM C 672
25 cycles	CaCl ₂ : 0.003	NaCl: 0.067		
50 cycles	CaCl ₂ : 0.005	NaCl: 0.084		

¹Typical results from air cured samples.

²Typical results from 3 days moist-cured and 39 days air-cured samples.

Results were obtained when material was mixed with 0.52 gallons (2 L) of water per bag and cured at 72° F (22° C). Expect reasonable variations, depending upon mixing equipment, temperature, application methods, test methods, and curing conditions.

CORRODED REINFORCING STEEL

1. Remove all oxidation and scale from the exposed reinforcing steel in accordance with ICRI Technical Guideline No. 03730 "Guide to Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion."
2. For additional protection from future corrosion, coat the prepared reinforcing steel with Emaco® P24 rebar coating or install Corr-Stops® CM galvanic anodes.

Mixing

1. Use a minimum 1/2" slow-speed drill and mixing paddle or an appropriately sized mortar mixer. Do not mix by hand.
2. Allow approximately 30 minutes to mix, place, and finish Emaco® T430 repair mortar at 72° F (22° C).
3. Pour 1/2 gallon (1.9 L) of clean water per bag of Emaco® T430 into mixer.
4. Add the powder to the water and mix approximately 3 – 5 minutes. Add small amounts of additional water as needed ONLY AFTER THE FIRST 2 MINUTES OF MIXING. No more than 1 pint of additional water per bag should be required to achieve a flowable mortar. Mix an additional 2 minutes after adding extra water.
5. Use neat material for patches less than 1" (25 mm) in depth. Do not use Emaco® T430 for patches less than 1/2" (13 mm) deep.
6. For deeper patches, a 55 lb (25 kg) bag of Emaco® T430 may be extended by adding up to 30 lbs (13.6 kg) of thoroughly washed, SSD, sound, non (ASR) reactive 1/4 – 1/2" (6 – 13 mm) rounded aggregate. When using angular aggregate, reduce the maximum amount added to 25 lbs (11.4 kg) to obtain the proper workability.

Application

1. After removing all standing water, thoroughly scrub a thin layer of bond coat into the saturated surface with a stiff-bristle broom or brush. Do not dilute the bond coat with water. A suitable bonding agent may be used instead. Do not apply more of this bond coat than can be covered with mortar before the bond coat dries. Do not retemper the bond coat.
2. Immediately place the repair mortar from one side of the prepared area to the other. Work the material firmly into the bottom and sides of the patch to ensure good bond. Level the Emaco® T430 mortar and screed it to the elevation of the existing concrete. Apply the appropriate finish.

3. The application range of Emaco T430 is from 20 to 100° F (-7 to 38° C). Follow ACI-recommended concreting practices for hot or cold weather.
4. For temperatures below 85° F (29° C), use Emaco® T415 in place of Emaco® T430.

Curing

If a topcoat will not be applied over Emaco® T430, wet cure for a minimum of 1 day, followed by the application of an ASTM C 309 or ASTM C 1315-compliant curing compound. Wet curing for longer than 1 day, even up to 28 days, minimizes shrinkage and cracking and improves physical properties.

TOPCOATING

1. BASF has a wide range of polymer flooring products for topcoating. Contact your local representative for more information.
2. For epoxy systems, allow 6 hours at 72° F (22° C) before topcoating. For polyester or vinyl ester systems, allow to cure 24 hours at 72° F (22° C) before priming and topcoating. For information on surface preparation, refer to the relevant data sheet.

Clean Up

Use water to remove repair mortar as soon as possible from tools and mixing equipment. Cured material can only be removed mechanically. Periodically clean tools and equipment during application.

For Best Performance

- Precondition these materials to approximately 70° F (21° C) for 24 hours before using.
- Use Confilm® evaporation reducer to protect repairs from direct sunlight, wind, and other conditions that could cause rapid drying of material.
- Minimum application thickness is 1/4" (6 mm).
- Do not use where applications require featheredging.
- Low material and placement temperatures may accelerate setting times. Increased mixing time with higher shear may help to lesson this phenomenon.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

EMACO® T430

Caution

Contains silica, crystalline quartz, fly ash, Portland cement, limestone, sodium sulfate.

Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

Precautions

Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Waste Disposal Method

This product when discarded or disposed of is not listed as a hazardous waste in federal regulations. Dispose of in a landfill in accordance with local regulations.

For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Material Safety Data Sheet (MSDS) on the job site or contact the company at the address or phone numbers given below.

Proposition 65

This product contains material listed by the State of California as known to cause cancer, birth defects or other reproductive harm.

VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517
Technical Service 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019950 7/07
Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF
Printed in U.S.A.